



# GFL 3030 & GFL 3040

## Gap Filler Liquid

**NEW  
OPTION**

Properties	Unit	GFL 3030	GFL 3040
Colour		green	lilac
Basic material		silicone	silicone
Mixing ratio		1 : 1	1 : 1
Curing		1h ;RT	1h ;RT
<b>Thermal Properties*</b>			
Thermal resistance $R_{th}$	K/W	0.82	0.58
Thermal conductivity $\lambda$	W/mK	3.0	4.3
<b>Electrical Properties**</b>			
Dielectric breakdown voltage $U_{d, ac}$	kV	6.0	5.0
<b>Mechanical Properties</b>			
Hardness	Shore 00	65 - 85	65 - 85
<b>Physical Properties</b>			
Application temperature	°C	-40 to +200	-40 to +200
Density	g/cm <sup>3</sup>	2.94	3.05
Viscosity***	Pas	50 - 80	55 - 85
Total mass loss (TML)	Ma. -%	< 0.06	< 0.09
Flame rating	UL-94	V-0	V-0
Possible thickness	mm	0.2 - 5.0	0.2 - 5.0

\* Measured @ thickness 1 mm    \*\* Measured @ thickness 0.5 mm    \*\*\* Shear rate 4s<sup>-1</sup> / 25°C

Ceramic filled, solvent free two component silicone elastomer. Room temperature curing makes it suitable for wet in wet production.

### Optionally available as GFL 3030 LV

- ✓ Extra low viscosity with 30-55 Pas
- ✓ Same properties except viscosity
- ✓ This variant is not thixotropic
- ✓ Self-levelling character

### Customer benefit

- ✓ A professional service-provider for dispensing production and technology
- ✓ A more economical dispensing material compared to conventional thermal pastes and tapes
- ✓ A time-saving, easy assembly due to the prefabricated, ready dispensed components

Data for engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

**NOTE:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. KERAFOL® is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. All specifications are subject to change without notice. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded. In case KERAFOL® would be nevertheless held liable, on whatever legal ground, KERAFOL®'s liability will in no event exceed the amount of the concerned delivery. All KERAFOL® products are sold pursuant to the KERAFOL®'s Terms and Conditions of sale and delivery in effect from time to time, a copy of which will be furnished upon request.

**11-2022**