



# PCM 20

## KERATHERM® phase-change

**NEW**

### Applications

- ◆ Notebooks
- ◆ Desktop CPU's
- ◆ IGBT units

### Benefits

- ◆ filling of smallest irregularities between the power module and heat sink
- ◆ melts at various temperatures
- ◆ improves the contact between the surfaces and increases the heat transfer
- ◆ special design for easy use and storage

Properties	Unit	PCM 20
Colour		grey
Compound		filled hot-setting wax
<b>Thermal Properties</b>		
Thermal resistance $R_{th}$	K/W	0.5
Thermal conductivity $\lambda$	W/mK	2.0
<b>Mechanical Properties</b>		
Measured thickness (+/-10%)	mm	0.4
Hardness	Shore A	55 - 65
Softening interval	°C	> 60
<b>Physical Properties</b>		
Application temperature	°C	up to 120°C
Density	g/cm <sup>3</sup>	1.4
Possible thickness	mm	in development

Phase-Change-Materials smooth out even the smallest irregularities between the power module and heat sink, thereby improving surface contact and increasing the heat transfer.

Data for engineer guidance only.  
Observed performance varies in application.  
Engineers are reminded to test the material in application.

**NOTE:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. KERAFOL® is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. All specifications are subject to change without notice. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded. In case KERAFOL® would be nevertheless held liable, on whatever legal ground, KERAFOL®'s liability will in no event exceed the amount of the concerned delivery. All KERAFOL® products are sold pursuant to the KERAFOL®'s Terms and Conditions of sale and delivery in effect from time to time, a copy of which will be furnished upon request.

**06-2022**