

GFL 2400 SL

Gap Filler Liquid

Benefits

- Room temperature curing
- Higher thermal conductivity in comparison to potting material
- Usage for Encapsulation, electromagnetic coils and applications with small fabrication tolerances
- Low Viscosity Gap Filler Liquid



Properties	Unit	GFL 2400 SL
Colour		green, blue
Basic material		silicone
Mixing ratio		1:1
Curing	°C	90-135 min; 25 °C
Thermal Properties*		
Thermal resistance R_{th}	K/W	< 1.02
Thermal conductivity λ	W/mK	> 2.4
Electrical Properties**		
Dielectric breakdown voltage $U_{d,ac}$	kV	> 7.5
Mechanical Properties		
Hardness	Shore 00	30 - 50
Physical Properties		
Application temperature	°C	-40 to +200
Density	g/cm ³	2.6
Viscosity	Pas	8 - 20
Total mass loss (TML)	Ma. -%	tbd
Flame rating	UL-94	V-0 (self-test)
Possible thickness	mm	0.2-5.0

* Measured @ thickness 1mm ** Measured @ thickness 0.5 mm