Keraex Sinter-Plates

PRELIMINARY DATA SHEET

Applications

- Sinter-Plates für the metal injection moulded (MIM) debinding and sintering process.
- Sinter-Plates for the LTCC & HTCC debinding and sintering process.
- · Sinter-Plates for the dental ceramics
- Sinter-Plates for the ceramic injection moulded (CIM) debindung sintering process
- Diaphragma for gas-sensors

Advantages

- $\cdot\,$ Save of energy costs due to lowder weight
- Save of process time due to good thermal shock resistance
- Increased yield
- smoother surfaces
- Fine porous structure
- High alumina content with (>99% Al_2O_3)
- Low or even no contact reactions with your materials
- No high tooling costs due to our process of using a ceramic tape
- Use one plate for debinding and sintering, no extra shelves

Typical characteristics	Unit	Value
Porosity	Vol.%	32 - 35
Surface roughness R_a	μm	< 2.0
Purity alumina	%	> 99
Bending strength	MPa	70
Camber	%	< 0.3
Temperature	°C	max. 1300

We cut the material according to your wishes! Please send in your CAD data.



Fine grainsized porous high alumina ceramic plate with a brought field of applications and outstanding properties

kerafol.com



Note

Disclaimer of Warranties and Limitation of Liability

The specifications provided in this data sheet do not constitute a guarantee or warranty of specific product properties ("quality guarantee"). These specifications are derived from our standardized testing procedures conducted under controlled laboratory conditions and are intended to describe the typical properties of the products as expected under standard applications. Variations may occur depending on the specific application. Accordingly, it is the responsibility of the customer to test and evaluate the products for their intended use, and adjustments to the application may be required.

The customer assumes full responsibility for the safety and functionality of their applications in which these products are integrated. Appropriate safety measures must be implemented to prevent bodily injury, fire, or other damages resulting from product defects. The customer is also responsible for ensuring that the design of their application comples with all applicable laws, regulations, codes, and standards. Unless expressly authorized by us in writing, our products must not be used in any application where product failure or the consequences there of could reasonably be expected to result in personal injury or harm. We make no representations, warranties, or assurances regarding the accuracy, completeness, or suitability of the information contained herein, including, without limitation, any warranty of non-infringement of third-party intellectual property rights.

We disclaim all liability arising from the application or use of the products described in this document. This document does not grant any license, express or implied, under any patents, copyrights, trade secrets, or other intellectual property rights, whether ours or those of third parties. Furthermore, we make no warranty or guarantee against potential infringement of third-party intellectual property rights arising from the use or application of our products.

Products may contain substances subject to regulatory labeling requirements; such information is provided in the corresponding safety data sheets. This document supersedes all prior information and may be updated or replaced at our discretion. We reserve the right to make changes to this document without notice.

12-2024